



MC Part #: [REDACTED]
 MC Lot #: [REDACTED]
 Material Type: [REDACTED]
 Material Lot Number: [REDACTED]
 Specimen Age (Days): 0
 Lab Temp: 69.0 °F
 Lab RH %: 8.00 %

Customer: [REDACTED]
 Customer PN: [REDACTED]
 Batch End Date and Time: [REDACTED]
 Operator: KJM
 Gage Length: 25.0 mm
 Initial Speed: 500 mm/min
 Speed: 500 mm/min
 Strain Point1: 0.30 %

Sample Number	Diameter mm	Inner Diameter mm	Area mm ²	Maximum Force N	Maximum Stress N/mm ²	Break Distance mm	Break Modulus Elongation N/mm ² %
1.00	1.32	0.700	0.984	63.6	64.7	129	526217
2.00	1.32	0.700	0.984	61.6	62.6	116	472260
3.00	1.32	0.700	0.984	61.6	62.7	121	496189
4.00	1.32	0.700	0.984	62.0	63.0	112	454270
5.00	1.32	0.700	0.984	66.3	67.4	132	538195
Average				63.0	64.1	122	497
SD				2.02	2.06	8.44	35.3



F-QMP-1801-1 Tensile Test Report

(ECO # 18009, Aug 6 2018) Revision: -